










## UNIMARBLE BIANCO

	<b>Origin</b>	Asia
	<b>Petrographic classification</b>	Engineered Marble
	<b>Appearance</b>	Unimarble® is an engineered marble composed of marble and limestone grains with polyester-resin as a binder.
	<b>Alternative names</b>	

### Usage

<b>General</b>	<p>The stone and surface finish should be selected depending on the intended use.</p> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; background-color: black; color: white; text-align: center; padding: 5px;"><b>Internal Applications</b></td> <td style="width: 50%; background-color: black; color: white; text-align: center; padding: 5px;"><b>Outdoor Applications</b></td> </tr> <tr> <td style="padding: 10px;"> <ul style="list-style-type: none"> <li>- Wall cladding</li> <li>- Decorative cut-to-size</li> <li>- Stairs</li> <li>- Shower</li> </ul> </td> <td style="padding: 10px; text-align: center;">not suitable for external applications</td> </tr> </table>		<b>Internal Applications</b>	<b>Outdoor Applications</b>	<ul style="list-style-type: none"> <li>- Wall cladding</li> <li>- Decorative cut-to-size</li> <li>- Stairs</li> <li>- Shower</li> </ul>	not suitable for external applications
<b>Internal Applications</b>			<b>Outdoor Applications</b>			
<ul style="list-style-type: none"> <li>- Wall cladding</li> <li>- Decorative cut-to-size</li> <li>- Stairs</li> <li>- Shower</li> </ul>			not suitable for external applications			
<b>Applications</b>						
<b>Recommendations</b>						

Hardness (Mohs)	Weight	Water absorption	Porosity
			
3-4	2520 kg/m <sup>3</sup>	0,02 %	NPD*
	EN 1936	EN 13755	
Compressive strength	Flexural strength	Wear resistance	FROSt RESISTANCE
			
125,4 MPa	22,8 MPa	22,0 mm	NPD*
EN 1926	EN 12372	EN 14157	

NPD\*: geen technische gegevens beschikbaar - no technical data available - pas d' informations techniques disponibles

### Observations and recommendations

<ul style="list-style-type: none"> <li>- Shades of color and / or granulometry may be present between the different batches and even within the same batch.</li> <li>- Small pigment "spots" may sporadically occur but have no technical disadvantages.</li> <li>- ATTENTION: this material is not heat-resistant for higher temperatures. Do not put a hot pan or pot directly on the surface!</li> <li>- Due to the mineralogical composition, this material is not resistant to acids.</li> <li>- This material cannot be used for exterior applications, since it is not UV-resistant (the colour changes when exposed to direct sunlight).</li> </ul>
---

# UNIMARBLE BIANCO

## Installation

<b>General</b>
<b>Installation system</b>
<b>Joint Width</b>

General procedures of good workmanship should be followed when laying the tiles (cfr. BBRI: Belgian Building & Research Institute ref. 137 Guide for Installing - Natural Stone and ref. 213). Immediately after delivery, the material will be stored indoors or at least protected from rain, wind and frost. If slabs are damaged or broken, the supplier must be informed before installation. They will then be used, as far as possible, against walls or for certain cuts.

Before installation, the installer will examine the slabs (previously dried) with the client and / or the architect to check for any deviations from the samples. The slabs will be carefully mixed before laying, in order to obtain a harmonious distribution of colors and various shades of the material.

Important: "Installation means acceptance!", It means that AFTER the installation, no more claims will be possible, except for hidden defects.

Flooring Inside	Exterieur Flooring
<p>For floor and wall applications, an adapted glue has to be used on a dry sub-surface (counter-floor).</p>	<p>Not suitable for outdoor paving</p>

3 - 5 mm (sawn edges)

When using silicones for filling joints between pieces, take care that the compound stone surface is well protected with tape, since traces of silicones are hard to remove.

## Maintenance

<b>General</b>
<b>First cleaning</b>
<b>Regular maintenance</b>
<b>Protection</b>
<b>Recommendations</b>

For more information on maintenance, see the document entitled "Care instructions" (available from us). We recommend that you follow these instructions so as not to damage the stone. The products used must be suitable for the materials. Follow the manufacturer's advice. In general, it must be stated that no moisture may be exaggerated when maintaining natural stone!

After installation, it is recommended to clean the surface with a strong cleaner or for example acetone (to remove possible greasy stains or stains from installation products). For floors, the cement remains must be removed with an adapted cleaner.

For regular maintenance, it is important not to use greasy products to avoid the formation of a superficial greasy layer.

For polished agglomerated stone materials, an extra impregnation product is normally not necessary. When an extra impregnation product is desired, one can apply a water-based impregnation product. For the brushed finishes, it is recommended to apply an extra impregnation product.

Do not use any acid-based products for the maintenance of this natural stone. Since the material is very compact, sometimes "stains" can be formed ON the surface. Such "stains" are usually easy to remove with a neutral detergent. For possible encrusted stains, it is recommended to remove the hardened part with a plastic knife or wooden spatula (do not use a metal knife), and the rest can be removed with a detergent (if necessary, use a mild alkaline product such as Lithofin MN Power-Clean).